



## Technical Data K-705 (A-J) Colored Glass Adhesive

UV based colored adhesive, low viscous.

### Base

- Modified urethane acrylate
- Single component, Solvent less liquid

### Use

- To be used for bonding Decorative Glass bonding
- Not to be used for Glass to Plastic bonding
- This product is normally used in a temperature range of -20° C to +100° C; depending on the application, other limits may be more reasonable
- Very good capillary properties

### Processing

- Supplied ready for use and can be processed well from the original container or we can custom size the packaging as per your requirement.
- The surface to be bonded must be dry as well as free of dust, grease and other contaminations
- For further information on how to apply, please see the Application Method.

### Technical Data

| Specification                     | K-705 Colored Adhesive |
|-----------------------------------|------------------------|
| Appearance                        | Colored                |
| Viscosity @ 25°C By F-Cup – B - 4 | 28 to 35               |
| Flash Point                       | >100°C                 |
| Specific Gravity @ 25°C           | 1.069                  |
| Refractive Index                  | 1.47 @ 25°C            |
| Full Curing Time                  | 85 - 95 Sec            |
| Shelf Life (Unopened)             | 1 Year                 |

### Curing

Using UV light with a wavelength of 320 – 400nm

The above information is based on our present knowledge and belief. Any conclusion and recommendation are made without liability on our part. Buyer & user should make their own assessment of our products under their own condition and for their own requirements.